



Medizay - PMMA BLOCK – Instruction for use

This product is a kind of homogeneous high polymer material made from quality polymethylmethacrylate added with cross-linking agents to improve the network structure through a unique polymerization moulding technology.

I. Application

This product is mainly used for the fabrication of multi-unit, fully or partially anatomical long-term temporary bridge restorations with up to two pontics by CAD/CAM systems. Both anterior and posterior crown & bridge are recommended.

II. Technical Parameters

Property	Parameter
Flexural strength	> 50MPa
Water absorption	<40ug/mm
Solubility	> 7.5ug/mm

III. Operational approaches

1. Procedure

After being milled by CAM, use a fine cross-cut tungsten carbide bur to cut off the lug. If white spots, which were caused by the diamond tools, can be seen on the surface after milling, these spots can be easily removed with a tungsten carbide bur without affecting the quality of the product. The restoration can be trialed on the working model to test its function of occlusion.

2. Polishing

Restorations can be pre-polished with a suitable silicone polisher and a small goat-hairbrush. Standard acrylic polishing agents that are also suitable for Intraoral use. Avoid creating excessive heat. Careful polishing is absolutely necessary to achieve a perfect result and avoid accumulation of plaque and the related negative effects on the shade.

3. Cleaning

Leaving the completed restoration in the ultrasonic unit for about 1 minute. Content of the alkaline cleaning solution: max.10%. Temperature:max.40C. Cleaning with steam results in heat and compressive stress and must generally be avoided.

4. Instalment inside the mouth

After preparing well for the repair at the repaired part of the patient, use the shade tabs to compare the shade and confirm the shade of the restoration. Seat the temporary restoration with a temporary adhesive cement and then remove excess materials. All provisional cements/adhesive materials are suitable. If the definitive restoration is to be cemented adhesively, eugenol free cementing materials must be used. Please observe the instructions of the respective manufacturers.

IV. Storage condition

This product should be stored in a dry and shade place, avoiding sunlight storage temperature: -18~33C.

V. Matters needing attention

1. Polymers must be worked on with a local dust extraction system.

2. Wear a dust mask and protective gasses to prevent the grinding dusts from being sucked into the mouth, entering into the eyes or contacting the mucosa.
3. The product should be used with caution if one is allergic to the acrylic resin materials.
4. Before being put into the patient's mouth, the restoration must be cleaned.
5. The restoration cannot be used for more than 6 months.
6. This product is a special material for the department of stomatology; a temporary restoration only can be used for one patient for one time and non professionals cannot use it. It should be put in a place where children cannot touch it.